

Material and Performance Specification

ECX-2[™] Double Net Excelsior Rolled Erosion Control Product

Description:

The ECX-2[™] is made with uniformly distributed 100% Aspen wood excelsior and two polypropylene nets securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECX-2[™] has functional longevity of approximately 24 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 1.5:1 and medium to high flow channels The ECX-2[™] meets Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

| Matrix: | | 1 | | 2 | | | |
|------------------|--|---------------------|---------|---------------------|---------------------|----------------------|--|
| | Aspen Wo | od Excelsior | | | | | |
| Netting: | Туре | | | | | Net Color | |
| Top: Lig | Top: Lightweight Photodegradable Polypropylene | | | | | Green | |
| Middle: No | one | | | | | | |
| Bottom: Lig | ghtweight Photodegrad | dable Polypropylene | | | | | |
| Net Opening: Top | | Mi | Middle | | Bottom | | |
| | 0.5" | x 0.5" | | | 0.5" > | : 0.5" | |
| Thread: | Туре | | Co | olor | | | |
| | Degradable Thread | | W | White | | | |
| Roll Sizes: | Standard | | "A" | "A" Size | | Mega | |
| Width: | 8 ft | 2.4 m | 4 ft | 1.2 m | 16 ft | 4.9 m | |
| Length: | 112.5 ft | 34.3 m | 225 ft | 68.6 m | 112.5 ft | 34.3 m | |
| Weight*: | 64 lbs | 29.0 kg | 64 lbs | 29.0 kg | 128 lbs | 58.1 kg | |
| Area: | 100 yd² | 83.6 m ² | 100 yd² | 83.6 m ² | 200 yd ² | 167.2 m ² | |
| #/Pallet: | 2 | 20 | | 9 | 2 | 0 | |

*Weight at time of manufacturing.

| Index Value Properties | *: | | | | | |
|-------------------------------|-------------|-------------------------|------------|--|--|--|
| Property | Test Method | Ту | Typical | | | |
| Mass/Unit Area | ASTM D6475 | 9.00 oz/yd ² | 305.1 g/m2 | | | |
| Thickness | ASTM D6525 | 0.38 in | 9.65 mm | | | |
| Tensile Strength-MD | ASTM D6818 | 169 lb/ft | 2.47 kN/m | | | |
| Elongation-MD | ASTM D6818 | 23 % | | | | |
| Tensile Strength-TD | ASTM D6818 | 86 lb/ft | 1.26 kN/m | | | |
| Elongation-TD | ASTM D6818 | 26.0 % | | | | |
| Light Penetration | ASTM D6567 | 36 % | | | | |
| Density / Specific Gravity | ASTM D792 | N/A g/cm ³ | | | | |
| Water Absorption | ASTM D1117 | 171 % | | | | |
| | | | | | | |

*May differ depending upon raw material variations

| Property | Test Method | | Value 0.04 | |
|------------------|-------------|---------|----------------------|--|
| C-Factors | ASTM D | | | |
| Slope Length (L) | ≤ 3:1 | 3:1-2:1 | ≥ 2:1 | |
| < 50 ft (15 m) | 0.035 | 0.144 | 0.272 | |
| 50 ft – 100 ft | 0.100 | 0.172 | 0.377 | |
| >100 ft (30 m) | 0.210 | 0.317 | 0.541 | |

*Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

| Test Method | Parameters | Results | |
|--------------------------------|---------------------------|-------------------------|--|
| | 50mm (2in) / hr-30 min | SLR**=6.69 | |
| ECTC Method 2 Rainfall | 100mm (4in) / hr-30 min | SLR**=5.18 | |
| | 150mm (6in) / hr-30 min | SLR**=3.99 | |
| ECTC Method 3 Shear Resistance | Shear at .50 in soil loss | 2.24 lb/ft ² | |

ECTC Method 4 Germination Top soil; Fescue; 21 day incubation 530 % *Bench scale tests should not be used for design purposes.

**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor

***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

| Property | Test Method | Value | | | |
|----------------------------|---------------|-------|---------------------|--------|-----|
| Unvegetated Shear Stress | ASTM D 6460 | 2.13 | lbs/ft ² | 101.98 | Ра |
| Unvegetated Velocity | ASTM D 6460 | 10.7 | ft/s | 3.26 | m/s |
| Vegetated Shear Stress | NA | N/A | lbs/ft ² | N/A | Ра |
| Vegetated Velocity | NA | N/A | ft/s | N/A | m/s |
| Manning's N (Value Represe | ents a Range) | | 0.02 | 26 | |

*Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

The values presented are for guidance purposes and do not constitute the practice of engineering. East Coast Erosion Blankets LLC (ECEB) ascertains that at the time of manufacture, all information presented herein is accurate and reliable and falls within the ECEB manufacturing product specification variances. If the product does not meet the stated values and ECEB is notified in writing prior to installation, the product will be replaced at no cost to the purchaser. ECEB will not be held liable for any type of damage or losses. directly or indirectly for failure of this product. Current revision supersedes all previous versions for this product.



5 Pine Camp Dr. Binghamton, NY 13904 Phone (

Phone (607) 729-5111 (800) 659-5111

1 Fax (607) 729-5158 www.iviindustries.com IVI-EC-3221-0310-C137