



Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506

1.800.582.4005 +1.610.488.8496 Fax +1.610.488.8494



Material and Performance Specification

ECP-2™ Polypropylene Turf Reinforcement Mat

Description:

The ECP-2™ is made with uniformly distributed 100% green polypropylene fiber and two medium weight polypropylene nets securely sewn together with UV stabilized thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECP-2™ is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels. The ECP-2™ meets Type 5.A, 5.B, and 5.C specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.18.

Matrix:	1	2
	Green or Tan Polypropylene Fiber	

Netting:	Type	Net Color
	Top: Medium weight 5# PMSF UV Stabilized Polypropylene	Black
	Middle: None	
	Bottom: Medium weight 5# PMSF UV Stabilized Polypropylene	

Net Opening:	Top	Middle	Bottom
	0.5" x 0.5"		0.5" x 0.5"

Thread:	Type	Color
	UV Stabilized Thread	Black

Roll Sizes:	Standard		"A" Size		Mega	
Width:	8 ft	2.4 m	4 ft	1.2 m	16 ft	4.9 m
Length:	112.5 ft	34.3 m	225 ft	68.6 m	112.5 ft	34.3 m
Weight:*	75 lbs	34.0 kg	75 lbs	34.0 kg	150 lbs	68.0 kg
Area:	100 yd ²	83.6 m ²	100 yd ²	83.6 m ²	200 yd ²	167.2 m ²
#/Pallet:	9		6		9	

*Weight at time of manufacturing within specified tolerances.

Index Value Properties*:

Property	Test Method	Typical	
Mass/Unit Area	ASTM D6566	12.00 oz/yd ²	406.9 g/m ²
Thickness	ASTM D6525	0.40 in	10.16 mm
Tensile Strength-MD	ASTM D6818	400 lb/ft	5.84 kN/m
Elongation-MD	ASTM D6818	31 %	
Tensile Strength-TD	ASTM D6818	400 lb/ft	5.84 kN/m
Elongation-TD	ASTM D6818	19.0 %	
Light Penetration	ASTM D6567	18 %	
Density / Specific Gravity	ASTM D792	0.915 g/cm ³	
Water Absorption	ASTM D1117	0 %	
Resiliency	ASTM D6524	80 %	
UV Resistance	ASTM D4355	82 %	1000 hours

*May differ depending upon raw material variations

Slope Performance Design Values*:

Property	Test Method	Value	
C-Factors	ASTM D6459	0.01	
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1
< 50 ft (15 m)	0.012	0.025	0.092
50 ft – 100 ft	0.036	0.065	0.115
>100 ft (30 m)	0.080	0.108	0.145

*Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Bench-Scale Testing* (NTPEP***):

Test Method	Parameters	Results
	50mm (2in) / hr-30 min	SLR**=5.53
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=5.38
	150mm (6in) / hr-30 min	SLR**=5.22
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.72 lb/ft ²
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	469 %

*Bench scale tests should not be used for design purposes.

**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor

***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:

Property	Test Method	Value	
Unvegetated Shear Stress	ASTM D 6460	2.60 lbs/ft ²	124.49 Pa
Unvegetated Velocity	ASTM D 6460	10.0 ft/s	3.05 m/s
Vegetated Shear Stress	ASTM D 6460	12.0 lbs/ft ²	574.56 Pa
Vegetated Velocity	ASTM D 6460	20.0 ft/s	6.10 m/s
Manning's N (Value Represents a Range)		0.028	

*Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

The values presented are for guidance purposes and do not constitute the practice of engineering. East Coast Erosion Blankets LLC (ECEB) ascertains that at the time of manufacture, all information presented herein is accurate and reliable and falls within the ECEB manufacturing product specification variances. If the product does not meet the stated values and ECEB is notified in writing prior to installation, the product will be replaced at no cost to the purchaser. ECEB will not be held liable for any type of damage or losses, directly or indirectly for failure of this product. Current revision supersedes all previous versions for this product.

Revised 1/11/2016

Distributed By:



5 Pine Camp Dr. Binghamton, NY 13904

Phone (607) 729-5111

(800) 659-5111

Fax (607) 729-5158

www.iviindustries.com

IVI-EC-3421-0310-C146