



## TECHNICAL DATA SHEET

### IVI Containment Fabric ENVIRO 130 FR

PRODUCT TEST DATA		
Physical Property	Test Method	Typical Value
Fabric		Woven Polypropylene
Weight	ASTM D-3776	13.4 oz./sq. yd.
Tear Strength - Trap Method	ASTM D-5136	Warp: 62 lbs. Fill: 58 lbs.
Tensile Strength - Grab Method	ASTM D-5100	Warp: 246 lbs. Fill: 252 lbs.
Adhesion - Diagonal	ASTM D-751-79	Won't Strip
Adhesion - Cycles	ASTM D-5306	250
Hydrostatic	ASTM D-5512	350 psi
Cold Crack	ASTM D-5874	-10 F
Mildew - Tensile Loss	ASTM D-5762	< 10%
Intermit/Contin - Farenheit		180, 160
UV Resistance	ASTM G-77-QUV	500 hrs.
Flame Resistance	ASTM - 5903	Passed
Flame Resistance	NFPA - 701	AF - 1 sec. Char 4

The information presented herein, while not guaranteed, is to the best of our knowledge, true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.