



TECHNICAL DATA SHEET

IVI Containment Fabric E-Tarp 85% Black

PRODUCT TEST DATA		
Physical Property	Test Method	Typical Value
Fabric		Woven Polypropylene
Construction		20 x 17
Weight	ASTM D-3776	4.3 oz./sq. yd.
Tensile Strength - Grab Method	ASTM D-1682	Warp: 230 lbs. Fill: 160 lbs.
Tear Strength - Trapezodial Method	ASTM D-2261	Warp: 90 lbs. Fill: 70 lbs
Mullen Burst Strength	ASTM D-3786	435 psi
Puncture Strength	ASTM D-3787	100 lbs.
Elongation	ASTM D-1682	W - 18%
Permeability	ASTM D-737	450 cfm

The information presented herein, while not guaranteed, is to the best of our knowledge, true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.