



TECHNICAL DATA SHEET

IVI Containment Fabric E-Tarp 85% Black FR

PRODUCT TEST DATA		
Physical Property	Test Method	Typical Value
Fabric		Woven Polypropylene
Construction		20 x 17
Weight	ASTM D-5261	4.6 oz./sq. yd.
Thickness	ASTM D-5199	13 mils
Yarn Type		930 Denier UV
Tensile Strength - Grab Method	ASTM D-4632	MD: 325 lbs. CD: 200 lbs.
Trap Tear	ASTM D-4522	MD: 150 lbs. CD: 90 lbs.
Burst	ASTM D-3786	450 psi
Puncture Strength	ASTM D-4833	100 lbs.

The information presented herein, while not guaranteed, is to the best of our knowledge, true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.