



TECHNICAL DATA SHEET

IVI Containment Fabric E-Tarp 85% White FR

PRODUCT TEST DATA		
Physical Property	Test Method	Typical Value
Fabric		Woven Polypropylene
Weight	ASTM D-3776	5.7 oz./sq. yd.
Count		21 Ends, 22 Pics
Burst Strength	ASTM D-3786	490 psi
Tensile Strength - Grab Method	ASTM D-4632	Warp: 300 lbs. Fill: 265 lbs.
Puncture Strength	ASTM D-4833	100 lbs.
UV Resistance	XFTM 141H-6152	>86% - 500 hrs.
Permeability	ASTM D-737	375 cfm
Flame Resistance	FTM - LS123-B	Zero Burn
Flame Resistance	DOT 302	Passed

The information presented herein, while not guaranteed, is to the best of our knowledge, true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.