

TECHNICAL DATA SHEET

IVI VT AOT Turbidity Curtain

IVI Type IB VT AOT Turbidity Curtain is recommended for construction sites located in protected areas (ponds, shallow lakes, small streams, and marshes) that are exposed only to light winds and to current velocities of less than 1.5 feet per second. Minimum anchorage may be required to maintain perimeter configuration.

Standard Features

Flotation Fabric: Non-permeable, 18 oz. yellow PVC coated polyester

Permeable Curtain Fabric: Carthage 6%

Section Length: 50 LF or 100 LF

Heat sealed seams

5000# break strength webbing

#4 spur grommets every 12" on center on edge of curtain for connection

Other Specifications

Curtain Depth 3' to 10'


 $6"\,x\,6"$ EPS foam blocks providing 15 lbs per LF buoyancy, $\,5/16"$ ballast chain

Curtain Depth 11' to 14'

 $8" \times 8"$ EPS foam blocks providing 26.7 lbs per LF buoyancy, 5/16" ballast chain, Grommets every 5' for extra ballast weight

Curtain Depth 15' and above

12" x 12" EPS foam blocks providing 60 lbs per LF buoyancy, 5/16" ballast chain, Grommets every 5' for extra ballast weight



NOTES: Depth measured from top of flotation device to bottom of curtain. Specified fabrics will be supplied per order: Permeable and non permeable. Buoyancy increased when specified. Ballast chain increased when specified.

The IVI VT AOT Turbidity Curtain fabric meets or exceeds the following specifications:

| Physical Property | Test Method | Data | |
|-----------------------------|-------------|---|----------------------|
| Grab Tensile Strength | ASTM D-4632 | 370 x 250 lbs (1.65 x 1.11 kN) 15% | |
| Grab Tensile Elongation | ASTM D-4632 | | |
| Wide Width Tensile Strength | ASTM D-4595 | 225 x 145 lbs/in 2700 x 1740 lbs/ft | (39.41 x 25.40 kN/m) |
| Mullen Burst Strength | ASTM D-3786 | 450 psi (3100 kPa) | |
| Trapezoid Tear Strength | ASTM D-4533 | 100 x 60 lbs (0.45 x 0.27 kN) | |
| Puncture Strength | ASTM D-4833 | 120 lbs (0.53 kN) | |
| CBR Puncture | ASTM D-6241 | 950 lbs (4.23 kN) | |
| UV Resistance (@ 500 hrs) | ASTM D-4355 | 90% strength retained | |
| Permittivity | ASTM D-4491 | .28 sec- ¹ | |
| Flow Rate | ASTM D-4491 | 18 gal/min per sq ft (733 l/min per sq m) | |
| Percent Open Area | CW-22125 | 4-6% | |
| Apparent Opening Size | ASTM D-4751 | 70 US Sieve (0.212 mm) | |

The properties reported above are effective 08/01/10 and are subject to change without notice.

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.